

| Rivofast | Color Index No. | Color pigment Index no. | Oil Absorption | Specific Gravity | Bulk Density gm/cc | Bleeding | | | | | | Fastness | | | | Application | | | | | | Plastic Application | | | | | |
|----------|-----------------|-------------------------|----------------|------------------|--------------------|-----------------|---------------|---------------|--------|---------------------|-------------------|--------------|-----------------|----------------|-----------|-------------|-----------|---------------------|--------------------------|--------------------------|------------------------------|----------------------------|--------|------------------|-------------|-----------|---------|
| | | | | | | 5% NaOH/ 5% HCl | Ethyl Alcohol | Ethyl Acetate | Xylene | Methyl Ethyl Ketone | Mineral Terentine | 5% Soap Soln | 5% NaOH/ 5% HCl | Heat Stability | Migration | Full Tone | Tint Tone | N.C. Lacquer/Paints | Air drying Enamel paints | offset/Letter Press/inks | Polyamide based liquids/inks | Aqueous liquid paints/inks | Rubber | Textile printing | Plastic/PVC | H D PE_PP | ABS/ASA |
| RF 600 | 74160 | Blue 15:0 | 40 | 1.5 | 0.36 | 5 | 5 | 5 | 4 | 5 | 5 | 5 | E | 150° | 5 | 7-8 | 5 | N | M | R | N | N | R | R | R | M | N |
| RF 601 | 74160 | Blue 15:0 | 40 | 1.5 | 0.36 | 5 | 5 | 5 | 4 | 5 | 5 | 5 | E | 180° | 5 | 7-8 | 5 | N | M | R | N | N | R | R | R | M | N |
| RF 602 | 74160 | Blue 15:1 | 40 | 1.5 | 0.56 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | E | 280° - 300° | 5 | 7-8 | 5 | N | N | R | N | N | R | R | R | N | M |
| RF 603 | 74160 | Blue 15:3 | 54 | 1.6 | 0.44 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | E | N | 5 | 7-8 | 5 | M | N | R | M | M | - | R | R | R | M |
| RF 604 | 74160 | Blue 15:4 | 54 | 1.6 | 0.44 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | E | N | 5 | 7-8 | 5 | R | - | - | R | R | - | N | N | M | N |
| RF 700 | 74260 | Green 7 | 30 | 1.5 | 0.53 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | E | 220° | 5 | 7-8 | 5-6 | M | R | R | M | N | M | R | R | M | M |
| RF 701 | 74260 | Green 7 | 35 | 1.6 | 0.42 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | E | 280° | 5 | 7-8 | 5-6 | N | N | N | N | HR | N | HR | N | N | N |
| RF 702 | 74260 | Green 7 | 35 | 1.6 | 0.42 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | E | 280° | 5 | 7-8 | 5-6 | M | HR | N | N | HR | N | N | N | N | N |
| RF 703 | 74260 | Green 7 | 35 | 1.6 | 0.42 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | E | 280° | 5 | 7-8 | 5-6 | HR | M | N | N | R | N | N | N | N | N |
| RF 704 | 74260 | Green 7 | 35 | 1.6 | 0.42 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | E | 280° | 5 | 7-8 | 5-6 | N | N | N | N | N | R | M | R | HR | HR |
| RF 705 | 74260 | Green 7 | 35 | 1.6 | 0.42 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | E | 280° | 5 | 7-8 | 5-6 | N | N | N | N | N | R | M | HR | R | M |
| RF 706 | 74260 | Green 7 | 35 | 1.6 | 0.42 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | E | 280° | 5 | 7-8 | 5-6 | N | N | HR | M | M | N | N | N | N | M |
| RF 707 | 74260 | Green 7 | 35 | 1.6 | 0.42 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | E | 240° | 5 | 7-8 | 5-6 | N | N | R | M | HR | XH | N | XH | N | M |
| RF 708 | 74260 | Green 7 | 35 | 1.6 | 0.42 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | E | 240° | 5 | 7-8 | 5-6 | N | N | M | HR | M | XH | N | XH | N | N |

LEGEND:

E=EXCELLENT
 HR=HIGHLY RECOMMENDED
 R=RECOMMENDED
 M=MAY BE USED
 N=NOT RECOMMENDED

BLEEDING: (1-5 SCALE)

1=CONSIDERABLE
 5=NO BLEEDING
 XH=UNSTABLE



MFG. UNIT: B-6, MIDC, LOTE-PARSHURAM, KHED, DISTRICT-RATNAGIRI, MAHARASHTRA-415722. (INDIA)

TEL: +91 2356-272850 **MOB:** +91 9049999445

REG. OFFICE: 18/178, SANT TUKARAM ROAD, MUMBAI, MAHARASHTRA-400009. (INDIA)

RIVERSIDE IND. LTD. : MANUFACTURERS AND EXPOTERS OF ORGANIC PIGMENTS

